

JOTAPROFF PRIMA CLEAN 10



02.2010

Jotaproff Prima Clean 10 is a washable and durable acrylic emulsion paint for interior use. Use as undercoat and top coat where a silky matt finish is desired. Excellent for areas which require a scrubbable, hard wearing and stain resistant coating.

PHYSICAL DATA:

Type.....	Acrylic dispersion paint
Colour.....	White, A, B and C base
Gloss.....	10 silk matt
Viscosity.....	115 K.U., 160 cP
Specific gravity.....	1,37 White base
Solids by volume %.....	42
Flash point, degrees centigrade.....	
Flexibility.....	
Hiding power (ISO 3905).....	
Water vapour permeability (ASTM D 1653).....	
Adhesion.....	
Adhesion (ISO 4624), dry.....	
Adhesion (ISO 4624), wet.....	
Adhesion (ISO 4624), after drying.....	
Particle size.....	
pH value.....	
pH value ready-mixed solution.....	
Weather resistance.....	
Gloss retention.....	
Water resistance.....	
Chemical resistance.....	
Solvent resistance.....	
Abrasion resistance.....	

RECOMMENDATION FOR USE:

Film thickness, dry.....	40-60 micrometres - microns micrometres
Film thickness, wet.....	100-150 micrometres - microns micrometres
Recommended spreading rate.....	8-10 m ² /ltr
Recommended spreading rate, sawn wood	
Recommended spreading rate, planed wood	
Application methods.....	Roller, brush or high pressure spray
Guiding data for airless spray:	
Nozzle.....	0,53mm / 0,021"
Spray angle.....	65-80 degrees
Pressure at nozzle.....	Min. 15MPa / Min. 150 kg/cm ²
Drying times, (guiding data at 23 deg. C, 50% R.H.):	
Dust dry.....	hour
Dry to touch.....	1 hour
Interval between coats.....	2 hours

Dry to use.....	Fully cured after 4 weeks, depending upon temperature, humidity, ventilation and film thickness.
Reaction time.....	hours
Thinner/cleaning agent.....	Thinner/Cleaner: Water
Mixing ratio.....	
Pot-life.....	hours
Conditions during application.....	
Substrate.....	
Drying time before sanding.....	hours
Launching.....	

SAFETY DATA:

A Material Safety Data Sheet has been issued for this product.
 EU limit value for this product (cat. A/a): 30 g/l (2010). This product contains max 1g/l VOC..

FLAMMABILITY CLASSIFICATION:

Norway.....
 Sweden.....
 Denmark.....

MISCELLANEOUS:

Tinting.....	Add maximum 10 % of Jotun Tinting Colours.
Size of containers.....	2,7 and 9 litres
Remarks.....	Stir well. Air and surface temperature must be at least +10 °C. Frost-free freight and storage. Contents of cans with different production numbers must be mixed to avoid possible colour deviations.

DIRECTIONS FOR USE:

Preparation:

Plaster, concrete, mortar, plaster boards, glassfibre- and wallpapers must be cleaned and thereafter apply directly Jotaproff Prima Clean 10. Old glossy paint must be washed with a suitable detergent and lightly sanded. Bare metal and nail heads should be suitably primed.

Use:

Apply Jotaproff Prima Clean 10 well and distribute evenly.

Environmental labelling:

Jotaproff Prima Clean 10 approved by Norwegian Ecolabelling and satisfied the demands and qualifies for the use of the "Flower" and the "Swan" symbol.



Liquid paint must not be emptied into waterways or sewers. Deliver to proper environmental handling station.

The above information is given to the best of our knowledge based on laboratory tests and practical experience. However, as the product is often used under conditions beyond our control, we cannot guarantee anything but the quality of the product itself. We reserve the right to change the given data without notice.

Paint should be looked upon as a semi-manufacture. The result is dependent on construction, the condition of the substrate, pre-treatment, temperature, relative air humidity, application etc.
